

## MILL INSPECTION CERTIFICATE

|                                                                                                            |       |       |       |        |        |                            |        |       |     |     |     |     |     |     |  |
|------------------------------------------------------------------------------------------------------------|-------|-------|-------|--------|--------|----------------------------|--------|-------|-----|-----|-----|-----|-----|-----|--|
| CUSTOMER: <span style="border: 1px solid black; display: inline-block; width: 100px; height: 1em;"></span> |       |       |       |        |        | CONDITION:                 |        |       |     |     |     |     |     |     |  |
| Order No: 104142                                                                                           |       |       |       |        |        | GRADE: 316                 |        |       |     |     |     |     |     |     |  |
| STANDARD: EN 12385-4 (DIN 3055)                                                                            |       |       |       |        |        | DATE: July.31,2025         |        |       |     |     |     |     |     |     |  |
| DESCRIPTION: STAINLESS STEEL WIRE ROPES                                                                    |       |       |       |        |        | CHEMICAL COMPOSITION (WT%) |        |       |     |     |     |     |     |     |  |
| ELEMENTS                                                                                                   | C     | Si    | Mn    | P      | S      | Cr                         | Ni     | Mo    | Cu  | Al  | Ti  | V   | N   | Co  |  |
| SPECIFICATION                                                                                              | <0.08 | <1.00 | <2.00 | <0.045 | <0.030 | 16-18                      | 10-14  | 2-3   | *** | *** | *** | *** | *** | *** |  |
| RESULTS (PRODUCT)                                                                                          | 0.031 | 0.42  | 1.103 | 0.03   | 0.029  | 16.105                     | 10.012 | 2.014 | *** | *** | *** | *** | *** | *** |  |

  

| STRAND /<br>CONSTRUCTION | Diameter<br>(mm) |  | Direction<br>lay | lay length<br>(mm) | tensile strength<br>(Mpa) |        | Breaking force<br>(KN) |        |  |  |  |  |  |  |
|--------------------------|------------------|--|------------------|--------------------|---------------------------|--------|------------------------|--------|--|--|--|--|--|--|
|                          |                  |  |                  |                    | Standard                  | Result | Standard               | Result |  |  |  |  |  |  |
| 7*7                      | 3.0              |  | RHOL             | 19.5               | 1570                      | 1838   | 5.09                   | 6.42   |  |  |  |  |  |  |
|                          |                  |  |                  |                    |                           |        |                        |        |  |  |  |  |  |  |
|                          |                  |  |                  |                    |                           |        |                        |        |  |  |  |  |  |  |

  

|  |                                                                                                                                                                                                                                                               |
|--|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
|  | 1. WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HEREIN BEEN MADE IN ACCORDANCE WITH<br>THE RESULTS OF THE CONTRACT, AND CONFIRM TO THE SPECIFICATION ABOVE<br>2. THE CERTIFICATE SHALL NOT BE REPRODUCED EXCEPT FULL WITHOUT THE WRITTEN APPROVAL OF THE COMPANY |
|--|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

We want to point out that the installation of the a.m. part is not allowed until it has been clarified that the machine this part shall be used for correspond to the regulations of the EC machinery rule