

# INSPECTION CERTIFICATE

(EN 10204:2004-3.1)

NO : 260268748  
ORDERING COMPANY :  
ORDER NO : 110729/111228  
STANDARD : EN 12385-4

DATE : 11.02.2026  
Measured Dia (mm) : 8,25  
Nominal Dia (mm) : 8  
LAY : RHOL  
LUBRICATION : A1  
REEL NO : 1115147194

TENSILE STRENGTH (N/mm2) : 2160  
LENGTH (M) : 1000  
NET WEIGHT (Kg) : 301  
CONSTRUCTION : 8x19 S WSCC CDP  
COATING : GALVANIZED

1115147195  
1115140478  
1115140479  
1115140480

## CHEMICAL ANALYSE OF WIRE ROD:

| C %         | Si %      | Mn %      | P max% | S max% |
|-------------|-----------|-----------|--------|--------|
| 0,45 - 0,78 | 0,10-0,30 | 0,50-0,80 | 0,030  | 0,030  |

TURKEY origin.

## TEST RESULTS:

| Number of wires | Diameter (mm) | Tensile Strength (N/mm <sup>2</sup> ) | Bend test (Number) | Torsion test (Number) | Zinc (gr/m <sup>2</sup> ) | Test on knotted wire (daN) |
|-----------------|---------------|---------------------------------------|--------------------|-----------------------|---------------------------|----------------------------|
| 72              | 0,55          | 2259                                  | 21                 | 26                    | 54                        |                            |
| 72              | 0,32          | 2247                                  |                    |                       | 34                        | 11                         |
| 8               | 0,66          | 2234                                  | 14                 | 38                    | 71                        |                            |
| 12              | 0,41          | 2242                                  |                    |                       | 48                        | 17                         |
| 24              | 0,61          | 2252                                  | 17                 | 35                    | 69                        |                            |
| 4               | 0,68          | 2281                                  | 12                 | 33                    | 68                        |                            |
| 3               | 0,38          | 2239                                  |                    |                       | 34                        | 15                         |
|                 |               |                                       |                    |                       |                           |                            |
|                 |               |                                       |                    |                       |                           |                            |
|                 |               |                                       |                    |                       |                           |                            |

the material does not incorporate iron and steel products originated from Russia – acc EU 833/2014 –

We hereby certify that the commodity is inspected according to EN 12385 and found good in all respects as stated above.

Minumum Breaking Load : 64 KN  
Actual Breaking Load : 71 KN



We want to point out that the installation of the a.m. part is not allowed until it has been clarified that the machine this part shall be used for correspond to the regulations of the EC machinery rule