

INSPECTION CERTIFICATE

(EN 10204:2004-3.1)

NO : 26274466
ORDERING COMPANY :
ORDER NO : 117035
STANDARD : EN 12385-4

DATE : 09.07.2026
Measured Dia (mm) : 9,15
Nominal Dia (mm) : 9
LAY : RHOL
LUBRICATION : A1
REEL NO : 1115951794

TENSILE STRENGTH (N/mm²) : 2160
LENGTH (M) : 1000
NET WEIGHT (Kg) : 390
CONSTRUCTION : 8x19 S IWRC CDP
COATING : GALVANIZED

CHEMICAL ANALYSE OF WIRE ROD:

C %	Si %	Mn %	P max%	S max%
0,45 - 0,78	0,10-0,30	0,50-0,80	0,030	0,030

TURKEY origin.

TEST RESULTS:

Number of wires	Diameter (mm)	Tensile Strength (N/mm ²)	Bend test (Number)	Torsion test (Number)	Zinc (gr/m ²)	Test on knotted wire (daN)
72	0,62	2236	18	31	71	
72	0,36	2232			42	13
8	0,74	2206	23	29	75	
12	0,47	2243			54	21
24	0,68	2212	14	28	70	
4	0,76	2238	17	34	69	
3	0,44	2228			53	19

the material does not incorporate iron and steel products originated from Russia – acc EU 833/2014 –

We hereby certify that the commodity is inspected according to EN 12385 and found good in all respects as stated above.

Minimum Breaking Load : 81 KN
Actual Breaking Load : 90 KN



We want to point out that the installation of the a.m. part is not allowed until it has been clarified that the machine this part shall be used for correspond to the regulations of the EC machinery rule