

# INSPECTION CERTIFICATE

(EN 10204:2004-3.1)

NO : 26026435	DATE : 07.01.2026
ORDERING COMPANY :	Measured Dia (mm) : 11,44
ORDER NO : 107382	Nominal Dia (mm) : 11
STANDARD : EN 12385-4	LAY : LHOL
	LUBRICATION : A1
	REEL NO : 1114957154
TENSILE STRENGTH (N/mm2) : 2160	
LENGTH (M) : 1000	
NET WEIGHT (Kg) : 596	
CONSTRUCTION : 8x19 S IWRC CDP	
COATING : GALVANIZED	

**CHEMICAL ANALYSE OF WIRE ROD:**

C %	Si %	Mn %	P max%	S max%
0,45 - 0,78	0,10-0,30	0,50-0,80	0,030	0,030

TURKEY origin.

**TEST RESULTS:**

Number of wires	Diameter (mm)	Tensile Strength (N/mm <sup>2</sup> )	Bend test (Number)	Torsion test (Number)	Zinc (gr/m <sup>2</sup> )	Test on knotted wire (daN)
72	0,77	2257	20	35	72	
72	0,44	2233			54	19
8	0,89	2233	17	34	84	
24	0,43	2263			45	18
4	0,47	2246			45	21
32	0,66	2257	14	37	74	
32	0,36	2268			45	14
4	0,63	2269	13	28	75	
6	0,40	2260			45	16
1	0,45	2215			52	20

the material does not incorporate iron and steel products originated from Russia – acc EU 833/2014 –

We hereby certify that the commodity is inspected according to EN 12385 and found good in all respects as stated above.

Minumum Breaking Load	:	121	KN
Actual Breaking Load	:	124	KN



We want to point out that the installation of the a.m. part is not allowed until it has been clarified that the machine this part shall be used for correspond to the regulations of the EC machinery rule