

INSPECTION CERTIFICATE

(EN 10204:2004-3.1)

NO : 26269638
ORDERING COMPANY :
ORDER NO : 109344
STANDARD : EN 12385-4
DATE : 22.01.2026
Measured Dia (mm) : 15,45
Nominal Dia (mm) : 15
LAY : LHOL
LUBRICATION : A1
REEL NO : 1115022041
TENSILE STRENGTH (N/mm²) : 2160
LENGTH (M) : 1000
NET WEIGHT (Kg) : 1002
CONSTRUCTION : 8x26 WS IWRC CPI
COATING : GALVANIZED

C %	Si %	Mn %	P max%	S max%
0,55 - 0,78	0,10-0,30	0,50-0,80	0,030	0,030

TURKEY origin.

TEST RESULTS:

Number of wires	Diameter (mm)	Tensile Strength (N/mm ²)	Bend test (Number)	Torsion test (Number)	Zinc (gr/m ²)	Test on knotted wire (daN)
80	0,90	2248	14	35	83	
40	0,49	2231			49	23
40	0,63	2268	16	35	71	
40	0,54	2248	18	41	61	
8	0,41	2239			48	17
36	0,79	2250	21	34	71	
6	0,87	2265	13	36	82	
6	0,91	2221	12	36	78	
1	1,01	2254	22	26	84	

the material does not incorporate iron and steel products originated from Russia – acc EU 833/2014 –

We hereby certify that the commodity is inspected according to EN 12385 and found good in all respects as stated above.

Minimum Breaking Load : 218 KN
Actual Breaking Load : 222 KN



We want to point out that the installation of the a.m. part is not allowed until it has been clarified that the machine this part shall be used for correspond to the regulations of the EC machinery rule